

PRODUCT DESCRIPTION

A traditional yacht varnish with UV resistance. Features include excellent flexibility, ease of application, good gloss retention, and non-blooming qualities. A high clarity finish especially suited to lighter colour timbers.

PRODUCT INFORMATION

Colour	YVA202-Clear
Finish	Full gloss
Specific Gravity	0.93
Volume Solids	52%
Typical Shelf Life	2 yrs
VOC (As Supplied)	352 g/ltr
Unit Size	375 ml 750 ml 2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		15°C		23°C		35°C	
Touch Dry [ISO]	16hrs		10hrs		5hrs		3hrs	

	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Original	36hrs	5days	24hrs	4days	16hrs	2days	12hrs	1days

APPLICATION AND USE

Preparation	<p>PREVIOUSLY VARNISHED WOOD:</p> <p>In Good Condition: Clean with thinners. Sand smooth with 280-320 grade paper. Remove sanding dust with thinners.</p> <p>In Poor Condition: Remove all previous coatings.</p> <p>BARE WOOD: Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat.</p> <p>Priming bare wood: Apply Intertox or UCP. If UCP has been omitted thin the first coat by 10-15% with Thinners No.1.</p>
Method	Apply a minimum of 3 unthinned coats, more if using a roller.
Hints	<p>Mixing Stir well before use.</p> <p>Thinner YTA800, YTA085 Thinners No.1 Thinners No.3</p> <p>Cleaner YTA800 Thinners No.1</p> <p>Airless Spray Pressure: 176-210 bar. Tip Size: 1365-1580.</p> <p>Conventional Spray Pressure: 2-3 bar. Tip Size: 1.1-1.4 mm. Thin 25-30% with Thinners No.3</p> <p>Roller If applying by roller, lay off with a brush or pad otherwise air bubbles may become trapped in the film.</p> <p>Other For Airmix spray application: Pressure: 2 bar. Tip Size: 06-113. For best results sand lightly between coats with 320-400 grade paper. Avoid using direct from the can. Pour the amount you expect to use in a separate container.</p>
Some Important Points	Use above the waterline only. Do not use below 5°C. Avoid painting in direct sunlight. Product temperature should be minimum 15°C and maximum 35°C. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.

Compatibility/Substrates	Suitable for use on all types of wood except direct application on oily timbers such as Teak and Iroko.
Number of Coats	3 minimum
Coverage	(Theoretical) - 11.70 (m ² /lt)
Recommended DFT	40 microns dry by brush
Recommended WFT	77 microns wet by brush
Application Methods	Brush, Roller, Conventional Spray, Airmix, Airless Spray

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Original to be realised ensure that between use the container is firmly closed and the temperature is between 5° C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: Original should be kept in securely closed containers during transport and storage.</p>
Safety	<p>GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p>DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Original cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

IMPORTANT NOTES *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

<p>Head Office International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500</p>	<p>European Region International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne & Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977</p>	<p>Asia Region International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778</p>	<p>Australasia Region International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287</p>	<p>North America Region International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545</p>	<p>South America Region International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200</p>
---	--	--	--	--	--



Ref: 05000087
Issue Date: 4-Sep-2004
Supersedes: 14-Feb-2003